

[Learn More](#)**Manufacturer:**
ÅngströmBond®**Product Name:**
DeSolite® DP-1032 Primary Optical Fiber Coating, UV Cure (1 kg)**Manufacturer Part Number:**
COV-DP-1032-1KG

► Click here for more details on the DeSolite® DP-1032 Primary Optical Fiber Coating, UV Cure (1 kg)

Product Data



Next Generation Primary Coating

DeSolite® DP-1032

Product Description

Next Generation DeSolite® Supercoatings are developed for both Wet-on-Wet and Wet-on-Dry processes that provide superior microbending performance and robust field application.

Characteristics

Liquid Coating	Typical Properties
Viscosity, 25°C, mPa·s	4,465
Density, 23°C, g/cm³	1.055
Liquid Refractive Index, 20°C	1.488
Surface tension, 23°C, dynes·cm⁻¹	34

Mechanical Property (RTDMA*)	Typical Properties
Gel Time, sec	0.39
Plateau Modulus, MPa	0.35

Cured Coating* (Tested at <1% R.H.)	Typical Properties
Glass Transition Range (DMA***), °C at E' _{1000 MPa}	-42
Glass Transition Range (DMA***), °C at E' _{100 MPa}	-32

Cured Coating* (Tested at 23°C, 50% R.H.)	Typical Properties
Elongation, %	108
Tensile strength, MPa	0.6
Segment modulus, MPa	1.0

Product Benefits

- Enables high draw speeds
- Exceptional microbend performance
- High n_d for 2 pt. bending and tensile methods
- Excellent cavitation resistance
- Optimized adhesion for ribbon, loose-tube and aging performance

Cured Coating* (continued) (Tested at 23°C, 50% R.H.)	Typical Properties
Hydrogen generation (24 hrs, 80°C in air, 75 µm films, µl·g⁻¹)	0.0
Refractive Index	1.496
Adhesion to glass, 50% RH conditioning, g/in	43
Adhesion to glass, 95% RH conditioning, g/in	35

*Real Time Dynamic Mechanical Analysis

**75 µm films cured in nitrogen at 1.0 J·cm⁻² using one D lamp, unless stated otherwise. UV dose determined with an IL-390 radiometer manufactured by International Light, Inc.

***Dynamic Mechanical Analysis

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice. FOC last update 1/29/2026.



Learn More



Manufacturer:
ÅngströmBond®

Product Name:
DeSolite® DP-1032 Primary Optical Fiber Coating, UV Cure (1 kg)

Manufacturer Part Number:
COV-DP-1032-1KG

► Click here for more details on the DeSolite® DP-1032 Primary Optical Fiber Coating, UV Cure (1 kg)

Next Generation Primary Coating DeSolite® DP-1032



Test Methods

Test methods available upon request.

Filtration

DeSolite® Optical Fiber Coatings are manufactured using fine filtration techniques designed to minimize particulate matter and to ensure high strength and uniform product performance.

Storage Conditions

Protect DeSolite® coatings from all sources of ultraviolet light, including sunlight and fluorescent light, to prevent premature curing. It is recommended that DeSolite® coatings be stored in a dry place in unopened, undamaged, original containers at temperatures between 15°C and 30°C. Storage or shipment in cold conditions may result in a phase separation which is reversible and is corrected by heating for 24 hours at 50°C. If possible, the container should be gently rolled to assure uniform dissolution during this heating process.

Shelf Life

Recommended shelf life is 12 months from the date of manufacture, provided that the above stated storage conditions are properly maintained.

Safety Information

This product is formulated with multifunctional acrylates which may cause skin and eye irritation and/or skin sensitization. Safety data sheets for each product are available from your Fiber Optic Center sales representative. All safety and handling recommendations should be followed carefully.

Conversions

$N = g \cdot f \times 9.807 \times 10^{-3}$ $kg \cdot mm^{-2} = MPa \times 0.102$
 $psi = MPa \times 145$ $mpa \cdot s = cps$

ÅngströmBond® is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center™, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee – inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes. This warranty is limited to a credit or replacement of the product only, and does not cover direct, indirect, consequential, incidental or any other type of damage resulting from the use of the product. Fiber Optic Center is not liable for any failure to observe the precautionary measures described in this SDS or for any misuse of the product.

UPDATED 30-March-2025

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice. FOC last update 1/29/2026.



Learn More



Manufacturer:
ÅngströmBond®



Product Name:
DeSolite® DP-1032 Primary Optical Fiber Coating, UV Cure (1 kg)

Manufacturer Part Number:
COV-DP-1032-1KG

► Click here for more details on the DeSolite® DP-1032 Primary Optical Fiber Coating, UV Cure (1 kg)

Next Generation Primary Coating DeSolite® DP-1032

ÅNGSTRÖM**Bond**®



Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice. FOC last update 1/29/2026.