

## **Manufacturer:**

Dymax

## **Product Name:**

Dymax OP-54 Optical Adhesive, Fiber Optic Assembly, Clear/Straw Color, Lower Viscosity than OP-52, UV Cure - 3ml Syringe

**Manufacturer Part Number:** 

OP-54-3ML



Click here for more details on the Dymax OP-54 Optical Adhesive, Fiber Optic Assembly, Clear/Straw Color, Lower Viscosity than OP-52, UV Cure - 3ml Syringe



OPTICAL ADHESIVES
OP-54 Product Data Sheet

Learn More

# Light Weld® OP-54 Lens/Fiber Optics

Lower in viscosity than OP-52, fiber bundles can be unitized in a few seconds using Light Weld® OP-54 instead of the hours frequently required using other types of adhesives. Light Weld OP-54 may also be used as a clear potting adhesive, curing to depths of 0.25 inches or more, depending on the light source used.

Dymax high-performance optical adhesives cure upon exposure to UV or visible light in seconds. Because of their solvent-free and rapid-cure features, they increase productivity, lower assembly cost, and enhance worker safety. When cured with Dymax spot, beam or flood lamps, they deliver optimum speed and performance for a variety of optical applications. This product is in full compliance with RoHS directives 2015/863/EU.

SUBSTRATES BONDED: • Borosilicate Glass • Soda Lime Glass • ABS • Filled Nylon • Metal

• High-Strength Positioning Adhesive • Low Outgassing • Low Shrinkage

FEATURES: • Low Moisture Absorption • Heat Cycle Stable

• Non Movement During Cure or Thermal Excursions • Complete Cure in Seconds

APPLICATIONS: • Fiber Optics Splicing • Pig Tailing • Lens Bonding • Joining • Mounting Fiber Optics

## **TYPICAL UNCURED PROPERTIES**

Solvent Content

Composition

Appearance

None - 100% Solids

Urethane Acrylate

Clear/Straw Liquid

Solubility Alcohols/Ketones/Chlorinated Solvents

Flash Point >79°C (175°F)

Viscosity 105 cP (nominal) ASTM D-1084

## TYPICAL CURED PROPERTIES

**Durometer Hardness** D85 ASTM D-2240 Tensile at Break 8,700 psi ASTM D-638 ASTM D-638 Elongation at Break 6% Modulus of Elasticity 52,000 psi ASTM D638 Glass Transition, Tg 75°C ASTM F-831 58 x 10<sup>-6</sup> in/in/°C ASTM E-831 CTE  $\alpha_1$  (below  $T_g$ ) 162 x 10<sup>-6</sup> in/in/°C CTE  $\alpha_2$  (above T<sub>g</sub>) ASTM E-831 CTE (-50°C to 200°C) 226 x 10<sup>-6</sup> in/in/°C ASTM E-831 ASTM D-570 24 hr Water Absorption 0.5% ASTM D-2566 Linear Shrinkage 1.8 %

\*DSTM Refers to Dymax Standard Test Method



Contact the professionals at Fiber Optic Center for a quote or to get more details.





## **Manufacturer:**

Dymax

### **Product Name:**

Dymax OP-54 Optical Adhesive, Fiber Optic Assembly, Clear/Straw Color, Lower Viscosity than OP-52, UV Cure - 3ml Syringe

## **Manufacturer Part Number:**

OP-54-3ML



Click here for more details on the Dymax OP-54 Optical Adhesive, Fiber Optic Assembly, Clear/Straw Color, Lower Viscosity than OP-52, UV Cure - 3ml Syringe



## **OPTICAL ADHESIVES**


**OP-54 Product Data Sheet** 

#### CURF DATA

Lamp	2000-EC	5000-EC	PC-3	3010-EC
Light Type	UV	UV	UV	UV
Lamp Type	Flood	Flood	Spot	Spot
Intensity (mW/cm²) at Peak Wavelength	50 @ 365 nm	150 @ 365 nm	1000 @ 365 nm	1800 @ 365 nm
Wavelength (nm) Working Range	300 <b>-</b> 500	300-500	300-500	300-500
Cure Speed (sec)				
Between Glass	1	1	1	1
Bead	<10	4	1	1

### **OPTICAL PROPERTIES**





## **DISPENSING AND HANDLING ADHESIVE**

This material may be dispensed with a variety of manual and automatic applicators or other equipment as required.

## STORAGE AND SHELF LIFE

Store the material in a cool, dark place when not in use. Do not expose to light. This product may polymerize upon prolonged exposure to ambient and artificial light. Keep covered when not in use. This material has an 18-month shelf life from date of manufacture, unless otherwise specified, when stored between 10°C (50°F) and 35°C (90°F) in the original, unopened container.

### SAFETY

Wear impervious gloves and/or barrier cream. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. Do not wear absorbent gloves. Remove adhesive from skin with soap and water. Never use solvents to remove adhesive from skin or eyes.

### CAUTION

For industrial use only. Avoid breathing vapors. Avoid contact with eyes and clothing. In case of contact, immediately flush with water for at least 15 minutes; for eyes, get medical attention. Wash clothing before reuse. Keep out of reach of children. Do not take internally. If swallowed, vomiting should be induced at once and a physician called. For specific information, refer to the Material Safety Data Sheet before use.

# Contact the professionals at Fiber Optic Center for a quote or to get more details.



## **Manufacturer:**

Dymax



Dymax OP-54 Optical Adhesive, Fiber Optic Assembly, Clear/Straw Color, Lower Viscosity than OP-52, UV Cure - 3ml Syringe



OP-54-3ML



Click here for more details on the Dymax OP-54 Optical Adhesive, Fiber Optic Assembly, Clear/Straw Color, Lower Viscosity than OP-52, UV Cure - 3ml Syringe



OPTICAL ADHESIVES
OP-54 Product Data Sheet

Learn More

### **GENERAL INFORMATION**

This product is intended for industrial use only. Keep out of the reach of children. Avoid breathing vapors. Avoid contact with skin, eyes, and clothing. Wear impervious gloves. Repeated or continuous skin contact with uncured material may cause irritation. Remove material from skin with soap and water. Never use organic solvents to remove material from skin and eyes. For more information on the safe handling of this material, please refer to the Safety Data Sheet before use.

The data provided in this document are based on historical testing that Dymax performed under laboratory conditions as they existed at that time, and are for informational purposes only. The data are neither specifications nor guarantees of future performance in a particular application. Dymax does not guarantee that this product's properties are suitable for the user's intended purpose.

Numerous factors—including, without limitation, transport, storage, processing, the material with which the product is used, and the ultimate function or purpose for which the product was obtained—may affect the product's performance and/or may cause the product's actual behavior to deviate from its behavior in the laboratory. None of these factors are within Dymax's control. Conclusions about the behavior of the product under the user's particular conditions, and the product's suitability for a specific purpose, cannot be drawn from the information contained in this document.

It is the user's responsibility to determine (i) whether a product is suitable for the user's particular purpose or application and (ii) whether it is compatible with the user's intended manufacturing process, equipment, and methods. Under no circumstances will Dymax be liable for determining such suitability or compatibility. Before the user sells any item that incorporates Dymax's product, the user shall adequately and repetitively test the item in accordance with the user's procedures and protocols. Unless specifically agreed to in writing, Dymax will have no involvement in, and shall under no circumstances be liable for, such testing.

Dymax makes no warranties, whether express or implied, concerning the merchantability of this product or its fitness for a particular purpose. Nothing in this document should be interpreted as a warranty of any kind. Under no circumstances will Dymax be liable for any injury, loss, expense or incidental or consequential damage of any kind allegedly arising in connection with the user's handling, processing, or use of the product. It is the user's responsibility to adopt appropriate precautions and safeguards to protect persons and property from any risk arising from such handling, processing, or use.

Except as otherwise noted, all trademarks used herein are trademarks of Dymax. The "®" symbol denotes a trademark that is registered in the U.S. Patent and Trademark Office.

The contents of this document are subject to change. Unless specifically agreed to in writing, Dymax shall have no obligation to notify the user about any change to its content.

Contact the professionals at Fiber Optic Center for a quote or to get more details.