



Manufacturer:
Epoxy Technology

Product Name:
EPO-TEK® OG142-112 Low Viscosity Epoxy, UV Cure (3cc Syringe)

Manufacturer Part Number:
OG142-112-3CC

► Click here for more details on the EPO-TEK® OG142-112 Low Viscosity Epoxy, UV Cure (3cc Syringe)

EPOXY
* TECHNOLOGY

Date: June 2017 **Rev:** VIII
No. of Components: Single
Mix Ratio by Weight: N/A
Specific Gravity: 1.18
Pot Life: N/A
Shelf Life: One year refrigerated

NOTES:

- Container(s) should be kept closed when not in use.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity, others) of the Products may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.

EPO-TEK® OG142-112

Technical Data Sheet
For Reference Only
UV Cure Optical Epoxy

Recommended Cure
Iron-Doped Mercury Flood Lamp > 30 sec.
100 mW/cm² @ 240-365 nm

Alternative Cures*

Iron-Doped Mercury Spot Lamp > 90 sec.
365nm LED Flood Lamp > 90 sec.
Pulsed Mercury Lamp > 90 sec.

UV Cure is complete after 24 hours from

UV Exposure

* Contact Technical Services for application-specific variations

Product Description: EPO-TEK® OG142-112 is a single component, low viscosity epoxy for adhesive sealing and encapsulating fiber optic and opto-electronic packaging applications.

Typical Properties: *Cure condition: Varies as required *denotes test on lot acceptance basis Data below is not guaranteed. To be used as a guide only, not as a specification. Different batches, conditions & applications yield differing results.*

PHYSICAL PROPERTIES:

* Color (before cure):	Clear/Colorless
* Consistency:	Pourable liquid
* Viscosity (23°C) @ 100 rpm:	1,200 - 1,700 cPs
Thixotropic Index:	N/A
* Glass Transition Temp:	≥ 90 °C (Dynamic Cure:20-200°C/ISO 25 Min; Ramp -10-200°C @ 20°C/Min)
Coefficient of Thermal Expansion (CTE):	
Below Tg:	55 x 10 ⁻⁶ in/in°C
Above Tg:	158 x 10 ⁻⁶ in/in°C
Shore D Hardness:	83
Die Shear:	
UV Cure:	≥ 20 Kg 7,112 psi
UV Cure + 23°C/24 Hours:	28.1 Kg 9,992.4 psi
Degradation Temp:	384 °C
Weight Loss:	
@ 200°C	0.27 %
@ 250°C	0.81 %
@ 300°C	1.75 %
Suggested Operating Temperature:	< 300 °C (Intermittent)
Storage Modulus:	592,522 psi

OPTICAL PROPERTIES @ 23°C:

Spectral Transmission:	≥ 97% @ 500-1,660 nm
Refractive Index (uncured):	1.5374 @ 589 nm
Refractive Index (cured):	1.5560 @ 589 nm

Epoxyes and Adhesives for Demanding Applications™

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice. FOC last update 1/14/2026.



Learn More



Manufacturer:
Epoxy Technology

Product Name:
EPO-TEK® OG142-112 Low Viscosity Epoxy, UV Cure (3cc Syringe)

Manufacturer Part Number:
OG142-112-3CC

► Click here for more details on the EPO-TEK® OG142-112 Low Viscosity Epoxy, UV Cure (3cc Syringe)

EPOXY
* TECHNOLOGY

EPO-TEK® OG142-112

Technical Data Sheet

For Reference Only

UV Cure Optical Epoxy

EPO-TEK® OG142-112 Advantages & Suggested Application Notes:

- Semiconductor: glob top "fill" encapsulant over IC's and wire bonds. It can be potted into cavities or around die that utilize a dam or ring.
- Fiber Optic:
 - ◊ Securing fibers into V-grooves; mounting glass cover slip over v-groove arrays; adhesive for fiber/ lens arrays.
 - ◊ Adhesive for the PLC device onto optical bench.
 - ◊ Fiber splicing, coupling and joining. Active alignment of optics into package.
- Optics:
 - ◊ Adhesion to all types of glasses, Lexan polycarbonate, and many more plastics and laminates.
 - ◊ Adhesive in the beam-pathway; capable of transmitting light from 400 to 2000 nm range.
 - ◊ Bonding beam splitter cubes and prisms together.
 - ◊ Adhesion to micro molded lenses.
- Potting:
 - ◊ Sealing and weather-proofing the solar ribbon connections to the environment via glass framed CIGS PV modules.

Epoxies and Adhesives for Demanding Applications™
This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice. FOC last update 1/14/2026.