# SAFETY DATA SHEET (SDS)



## **Manufacturer:**

ÅngströmBond®

## **Product Name:**

ÅngströmBond® AB2902 Electrically & Thermally Conductive Silver Epoxy, Room Temperature & Heat Cure (2.5g)

# **Manufacturer Part Number:**

AB2902-2.5G

Click here for more details on the AngströmBond® AB2902 Electrically & Thermally Conductive Silver Epoxy, Room Temperature & Heat Cure (2.5g)

<u>ngström</u>Bond®

ÅngströmBond AB2902 Hardener

Adhesives

Advanced Polymers for High Tech Applications

#### 1. MATERIAL IDENTIFICATION

ÄngströmBond AB2902 Hardener **Product Name:** 

For product emergencies involving spill, leak, fire, exposure, or accident call CHEMTREC at (800) 424-9300. For all other inquiries call Fiber Optic Center™, Inc. at (800) 473-4237. **Emergency Phone:** 

2. COMPOSITION **Exposure Limits** OTHER ACGIH [LV-TW/ 100 <75 <25 Modified Aliphatic NE NE NE NE NE NE NE NE 3,6-diazaoctanethylenediamine
Teta, reaction products with propylene oxide 26950-63-0

#### 3. HEALTH HAZARDS IDENTIFICATION

Primary Routes of Exposure: Eves: Yes Skin: Yes Inhalation: Yes

Eye Contact: Corrosive to the eyes and may cause sever damage including blindness. Eyes may become irritated, red, or itchy.

Skin Contact: Causes skin burns, irritation and possible allergic reaction. Skin may become itchy, red or irritated. May cause allergic skin reaction.

Inhalation: Prolonged or repeated inhalation may cause lung damage and/or central nervous system disturbance:

Ingestion: Can burn mouth, throat and stomach. Can cause mouth, throat, esophageal, and gastrointestinal tract irritation. Corrosive and May cause sever and permanent damage to mouth, throat and stomach.

#### 4. FIRST AID MEASURES

Immediately flush eyes with plenty of water. Get medical attention, if irritation persists

Immediately wash skin with soap and plenty of water. Remove contaminated clothing. Get medical attention if symptoms occur. Wash clothing before reuse. Skin:

Remove to fresh air. If not breathing, give artificial respiration. If breathing is difficult, give oxygen. Get medical attention. Inhalation:

If swallowed, do NOT induce vomiting. Give victim a glass of water or milk. Call a physician or poison control center immediately. Never give anything by mouth to an unconscious person. Ingestion:

# 5. PHYSICAL AND CHEMICAL PROPERTIES

Boiling Point: Freezing Point: Specific Gravity: >320°E Clear Amber liquid Amine-like Not determined 1.020

## **6. STABILITY AND REACTIVITY**

**Chemical Stability:** Stable under normal conditions and use.

Conditions and Materials to Avoid:

Contact with acidic, basic or oxidizing materials. Avoid storage in open containers, exposure to open flame or uncontrolled exposure to heat, uncontrolled mixing or exposure to incompatible substances. Oxides of carbon, aldehydes, amines, aniline, acids and other organic substances may be formed during combustion. The chemical nature and quantity of decomposition by-products will vary widely depending on the conditions of combustions. Hazardous Decomposition Products: conditions of combustion

Uncontrolled mixing with resins may cause hazardous polymerization.

#### ACCIDENTIAL RELEASE MEASURES

Small Spills: Activate available exhaust ventilation equipment in the immediate spill area. Wipe up or absorb spilled material with paper towels or other absorbent material. Wash area with soapy water o remove residue. Collect absorbed material and water rinses in appropriate containers. Dispose of in accordance with current Federal, State, and local regulations.

Dike area to contain spill. Take precautions as necessary to prevent contamination of ground and surface waters. Recover spilled Emba area to contain spin. Take precaturing as necessary to prevent contamination of ground and surface waters. Recover spilled material on adsorbent, such as sawdust or vermiculite, and sweep into closed containers for disposal. After all visible traces, including ignitable vapors, have been removed thoroughly wet vacuum the area. Do not flush to sewer. If area of spill is porous, remove as much contaminated earth and gravel, ect. as necessary and place in closed containers for disposal.

Release Notes: Spill response operations must be conducted in accordance with the provisions of OSHA 29 CFR 191.120. Review the entire MSDS before

## AngströmBond® is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center™. Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY FITNESS OR OTHERWISE with respect to Fiber Optic Center", Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee – inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes. This warranty is limited to a credit or replacement of the product only, and does not cover direct, indirect, consequential, incidental or any other type of damage resulting from the use of the product. Fiber Optic Center is not liable for any failure to observe the precautionary measures described in this SDS or for any misuse of the product.

Rev. E 07/2025

Fiber Optic Center™, Inc., 23 Centre Street, New Bedford, MA, 02740-6322, USA

Toll Free: (800) IS-FIBER or (800) 473-4237 

Phone: (508) 992-6464 

Fax: (508) 991-8876 

Website: www.focenter.com

Data is subject to change without notice.

# Contact the professionals at Fiber Optic Center for a quote or to get more details.



# SAFETY DATA SHEET (SDS)



## **Manufacturer:**

ÅngströmBond®

## **Product Name:**

ÅngströmBond® AB2902 Electrically & Thermally Conductive Silver Epoxy, Room Temperature & Heat Cure (2.5g)

## **Manufacturer Part Number:**

AB2902-2.5G

Click here for more details on the ÅngströmBond® AB2902 Electrically & Thermally Conductive Silver Epoxy, Room Temperature & Heat Cure (2.5g)



ÅngströmBond AB 2902 Hardener Page 2 of 2

Adhesives

Advanced Polymers for High Tech Applications

# 9. HANDLING AND STORAGE

Minimize contact with unprotected skin and eyes and insure that adequate ventilation is provided in the work area. Store material in a cool, dry place. Keep container closed when not in use, avoid contact with eyes and prolonged or repeated contact with skin. Maintain good housekeeping practices. Keep container closed when not in use, store in a cool dry place away from heat and flames. Keep out of the reach of children and do not re-use the container

#### 10. FIRE FIGHTING MEASURES

FLAMMABLE PROPERTIES
Flash Point:

Explosive Limits:
Auto – Ignition Temperature:
Hazardous Decomposition Products:

Not determined Not determined

Oxides of carbon, aldehydes, amines, aniline, acids and other organic substances may be formed during combustion. The chemical nature and quantity of decomposition by-products will vary widely depending on the conditions of combustion.

EXTINGUISHING MEDIA and FIRE FIGHTING INSTRUCTIONS
Firefighters/rescue personnel should wear positive pressure self-contained
breathing apparatus and full protective equipment. Cool exposed containers with water to prevent buildup. If large
quantities of material are involved, evacuate area and fight fire from a safe distance.

Extinguishing Media: Use foam, dry chemical, carbon dioxide or fine water spray when fighting fires involving this material

<u>UNUSUAL FIRE AND EXPLOSION HAZARD:</u>
Decomposition and combustion products may be toxic. Closed containers may violently rupture under fire condition.

#### 11. EXPOSURE CONTROLS AND PERSONAL PROTECTION

Engineering / Ventilation Controls:

Respiratory Protection:

Skin Protection:

Provide effective mechanical exhaust ventilation to draw vapors, mists or fumes generated during processing away from the worker and prevent routine inhalation, especially during elevated temperature processing. away from the worker and prevent routine inhalation, especially during elevated temperature processing. Provide effective mechanical exhaust ventilation to draw vapors, mists or furmes generated during processing away from the worker and prevent routing inhalation, especially during elevated temperature processing. Ventilation must be sufficient to maintain airborne levels of Section 3 chemicals below their PEL/TLV values. A respiratory protection program that meets OSHA 1910.134 and ANSI 288.2 requirements must be followed whenever workplace conditions warrant a respirator's use. Wear impervious gloves and appropriate protective colohing or equipment to prevent prolonged or repeated contact with skin. Use good personal hygiene practices. Wash hands before eating, drinking, smoking, or using restroom facilities. Promptly remove contaminated clothing and launder thoroughly before reuse.

#### 12. REGULATORY INFORMATION

<u>TSCA</u>
The chemical components of this product are included in the TSCA Chemical Substance Inventory, as required.

SARA Title III (Superfund Amendments and Reauthorization Act) Acute: Yes Chronic: Yes

HMIS Hazards:

Health: 2 Flammability: 1

Reactivity: 0

**Fiber Optic Center**, **Inc.** urges each customer or recipient of this MSDS to study it carefully in order to become aware of and understand the hazards associated with the product. The reader should consider consulting reference works or individuals who are experts in ventilation, toxicology, and/or fire prevention, as necessary to use and understand the data contained in this MSDS.

To promote safe handling, customers and recipients should: 1 – notify their employees, agents, contractors, and others whom they know or suspect will use this material or the information in this MSDS and any other information regarding hazards or safety; 2 – furnish this same information to each of their customers for the product; and 3 – request their customers to notify their employees, customers and other users of the product of this information.

The information contained herein is based on the data available to **Fiber Optic Center**\*\*, **Inc.**, and is believed to be correct. However, **Fiber Optic Center**\*\*, **Inc.** makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. **Fiber Optic Center**\*\*, **Inc.** assumes no responsibility for injury from the use of the product described herein.

## $m ilde{A}$ ngström $m Bond ilde{R}$ is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center\*\*, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee – inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes. This warranty is limited to a credit or replacement of the product only, and does not cover direct, indirect, consequential, incidental or any other type of damage resulting from the use of the product. Fiber Optic Center is not liable for any failure to observe the precautionary measures described in this SDS or for any misuse of the product.

Fiber Optic Center", Inc., 23 Centre Street, New Bedford, MA, 02740-6322, USA Toll Free: (800) IS-FIBER or (800) 473-4237 • Phone: (508) 992-6464 • E-mail: sales@focenter.com Phone: (508) 992-6464 • Fax: (508) 991-8876 • Website: www.focenter.com

Data is subject to change without notice.

# Contact the professionals at Fiber Optic Center for a quote or to get more details.

