



Manufacturer:
ÅngströmBond

Product Name:
ÅngströmBond AB9070 High Refractive Index Adhesive (3cc)

Manufacturer Part Number:
AB9070-3CC

▶ [Click here for more details on the ÅngströmBond AB9070 High Refractive Index Adhesive \(3cc\)](#)



Adhesives

Advanced Polymers for High Tech Applications

ÅNGSTRÖMBOND® AB9070
High Refractive Index Adhesive

ÅNGSTRÖMBOND® AB9070 is a high refractive index matched adhesive that is recommended for bonding glass to glass and is good for polycarbonate. This adhesive is very rigid when fully cured.

Typical Properties:

Refractive Index	1.70
Color	Clear
Viscosity @ 25°C, cps	4800
Elongation at Failure	1.3%
Modulus of Elasticity (psi)	863
Tensile Strength (psi)	90,200
Hardness, Shore D	75
Operating Temp, °C	-15 to 100

% Optical Transmission:

@ 350nm	57.7%
@ 400nm	81.6%
@ 450nm	86.4%
@ 500nm	88.2%
@ 550nm	88.9%
@ 600-2000nm	90.0%

Full Cure: requires 6 joules/cm²
Cure with UV light: 315nm-395nm with peak absorption at 365nm.
Cue with Visible light: 400nm-420nm.

Note: Curing should be done in an oxygen free environment. The cure schedules will increase with increased thickness, lower UV light intensity and the presence of oxygen and water.

Storage and Shelf Life:

Store in a cool, dark place (-5-22°C) when not in use. Do not place in view of UV light source or sunlight. Material may polymerize upon exposure to ambient light. If refrigerated, allow the adhesive to come to room temperature before using.

ÅNGSTRÖMBOND® is a REGISTERED TRADEMARK of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center™, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee - inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

Rev. A 09/2016

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.