



Manufacturer:
ÅngströmBond

Product Name:
ÅngströmBond AB9098 UV Optical Adhesive (3cc)

Manufacturer Part Number:
AB9098-3CC

▶ [Click here for more details on the ÅngströmBond AB9098 UV Optical Adhesive \(3cc\)](#)



Adhesives

Advanced Polymers for High Tech Applications

ÅNGSTRÖMBOND® 9098
High Strength UV/Blue Light Cure Adhesive

Description:

ÅNGSTRÖMBOND® 9098 is a clear, yellow resistant, UV cure adhesive designed for bonding glass, ceramics, metals and most plastics. This low shrinkage adhesive offers a high Tg without the need for a heat post cure. It can withstand 85/85 testing and is excellent for high temperature and temperature cycling applications.

Handling Characteristics:

Cure time:

150-300 mW/cm² - 5-15 sec. @320-480nm

Note: Cure schedules can vary slightly with different applications. Speed of cure depends upon thickness and light intensity. Lamps emitting high levels of shortwave light are not recommended. Please use these numbers as a basis to develop a schedule suitable for the application.

Typical Properties:

Color:	Clear
Viscosity @ 25°C, cps:	500
Hardness, Shore D:	70
Linear Shrinkage, %	0.78
Elongation, %	61
Tensile, psi	3,900
Modulus, psi	82,000
CTE /°C, Below Tg / Above Tg	98 / 224
Operating Temperature, °C:	-20 to 150
Glass Transition, °C	115
Refractive index cured	1.50
Water Absorption, % (25°C, 24 hrs)	1.5

Storage and Shelf Life:

Store in a cool, dark place when not in use. Do not place in view of UV light source or sunlight. Material may polymerize upon exposure to ambient light. This product has a shelf life of 12 months.

ÅNGSTRÖMBOND® is a REGISTERED TRADEMARK of FIBER OPTIC CENTER, INC., NEW BEDFORD MA, USA

Fiber Optic Center™, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee -- inasmuch as conditions of use are beyond our control. The properties given are typical values and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

Rev C 12/2019

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.