SAFETY DATA SHEET (SDS)



Manufacturer:

ÅngströmBond®

Product Name:

ÅngströmBond® AB9195 Flexible Epoxy, Room Temperature & Heat Cure (2.5g)

Manufacturer Part Number:

AB9195-2.5G

Click here for more details on the AngströmBond® AB9195 Flexible Epoxy, Room Temperature & Heat Cure (2.5q)



ÅngströmBond® AB9195 Hardener

Adhesives

Advanced Polymers for High Tech Applications

1. MATERIAL IDENTIFICATION

Product Name:

Emergency Phone:

2. COMPOSITION

Hazardous Components

AngströmBond® AB9195 Hardener

For product emergencies involving spill, leak, fire, exposure, or accident call CHEMTREC at (800) 424-9300. For all other inquiries call Fiber Optic Center**, Inc. at (800) 473-4237.

Percent

Exposure Limits ACGIH OSHA

Abbreviations: N.E. = Not Established

3. HEALTH HAZARDS IDENTIFICATION

Primary Routes of Exposure:

Skin: Yes

TLV-TWA

N.E.

Inhalation: Yes

PEL N.E.

Severe eye and eyelid membrane irritation

Skin Contact: Will cause dermal burns.

Inhalation: Heated vapors may produce irritation, shortness of breath, and dizziness

CAS No.

Proprietary

Ingestion: Effects are not known

Other: Preexisting skin and eye disorders may be aggravated by exposure to this product. Individuals with preexisting skin or

lung allergies may experience increased allergy symptoms upon exposure to this product

4. FIRST AID MEASURES

Flush eyes thoroughly with water for 15 minutes while holding eyelids open. Seek medical attention.

Skin: Wipe excess from skin, and flush the affected area with water. Follow by washing with soap and water. Wash

contaminated clothing thoroughly before reuse. If irritation persists obtain medical attention

Inhalation: Remove to fresh air, and provide oxygen or artificial respiration if needed. Obtain medical attention.

Ingestion: Do NOT induce vomiting. Obtain medical attention.

5. FIRE FIGHTING MEASURES

FLAMMABLE PROPERTIES

> 190°F, estimated Explosive Limits:
Auto – Ignition Temperature:
Hazardous Decomposition Products: Not determined Not determined Carbon oxides

EXTINGUISHING MEDIA and FIRE FIGHTING INSTRUCTIONS

When sufficiently large quantities are present, firefighters should be equipped with full bunker gear, including a positive pressure, NIOSH approved, self-contained breathing apparatus. Fire-exposed containers may be cooled with water. **Extinguishing Media:** Use carbon dioxide, dry chemical, or water spray.

 $m ilde{A}$ ngström $m ilde{B}$ ond $m ilde{B}$ is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center***, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee – inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

Data is subject to change without notice.

Rev. A 7/2001

Contact the professionals at Fiber Optic Center for a quote or to get more details.



SAFETY DATA SHEET (SDS)



Manufacturer:

ÅngströmBond®

Product Name:

ÅngströmBond® AB9195 Flexible Epoxy, Room Temperature & Heat Cure (2.5g)

Manufacturer Part Number:

AB9195-2.5G

Click here for more details on the AngströmBond® AB9195 Flexible Epoxy, Room Temperature & Heat Cure (2.5q)



ÅngströmBond® AB9195 Hardener Page 2 of 3

Adhesives

Advanced Polymers for High Tech Applications

6. ACCIDENTIAL RELEASE MEASURES

Ventilate the spill area, and evacuate if necessary. Shut off the source of the leak if it is safe to do so. Remove all ignition sources. Dike and contain large spills. Absorb with clay, sand, or another suitable material, and dispose of properly.

Clean-up personnel should use adequate protective equipment.

7. HANDLING AND STORAGE

Store in a cool, dry place, away from ignition sources and high temperatures. Avoid contact with incompatible materials. Wear protective eyewear, chemical-resistant gloves, and other protective clothing as appropriate. Some curing agents, if mixed with this product in sufficiently large quantities, can cause exothermic reactions and runaway polymerization, yielding fumes which vary widely in composition and toxicity. Do not breathe fumes.

8. EXPOSURE CONTROLS AND PERSONAL PROTECTION

Engineering / Ventilation Controls: General ventilation may be acceptable under most conditions, although local ventilation is required

to control exposure whenever vapors, mists, or dusts are generated.

Respiratory Protection: When local ventilation is unavailable and airborne limits are exceeded, a NIOSH-approved respirator

for organic vapors, a supplied-air respirator, or a self-contained breathing apparatus is required.

Skin Protection: Impervious gloves and protective clothing should be worn as necessary.

Eye Protection: Chemical splash goggles or safety glasses with side shields should be worn as appropriate.

9. STABILITY AND REACTIVITY

Chemical Stability: Stable under normal conditions and use.

Conditions and Materials to Avoid: Carbon dioxide may cause decomposition.

Hazardous Decomposition Products: Carbon oxides, ammonia, nitrogen oxide, traces of phenol.

Hazardous Polymerization: Will not occur.

10. PHYSICAL AND CHEMICAL PROPERTIES

 Appearance / State:
 Pale yellow liquid
 Boiling Point:
 390°F

 Odor:
 Ammonical odor
 Freezing Point:
 Not determined

 pH:
 Not determined
 Specific Gravity:
 1.0

 Vap. Pressure (mmHG):
 < 1</th>
 Solubility in Water:
 Negligible

Vap. Density (air = 1): Not determined

11. TOXICOLOGICAL INFORMATION

This product is not known to have undergone toxicological testing.

12. DISPOSAL CONSIDERATIONS

Keep out of surface waters, sewers, and waterways entering or leading to surface waters. Notify authorities if any exposure to the environment occurs or is likely to occur. Utilize an appropriate disposal facility, in compliance with applicable federal, state, and local environmental control regulations.

ÄngströmBond® is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center***, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee — inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

Data is subject to change without notice.

7/2001

Contact the professionals at Fiber Optic Center for a quote or to get more details.



SAFETY DATA SHEET (SDS)



Manufacturer:

ÅngströmBond®

Product Name:

ÅngströmBond® AB9195 Flexible Epoxy, Room Temperature & Heat Cure (2.5g)

Manufacturer Part Number:

AB9195-2.5G

Click here for more details on the AngströmBond® AB9195 Flexible Epoxy, Room Temperature & Heat Cure (2.5q)



ÅngströmBond® AB9195 Hardener Page 3 of 3

Adhesives

Advanced Polymers for High Tech Applications

13. TRANSPORTATION INFORMATION

DOT/IATA Proper Shipping Name: Corrosive Liquid, N.O.S.

Hazard Class: 8 Packaging Group: III

14. REGULATORY INFORMATION

TSCA
The chemical components of this product are included in the TSCA Chemical Substance Inventory, as required.

SARA TITLE III

Section 313 – Toxic Chemicals

Pursuant to Section 313, this product does not contain any chemicals in a concentration equal to or greater than the de minimis level.

Fiber Optic Center**, Inc. urges each customer or recipient of this MSDS to study it carefully in order to become aware of and understand the hazards associated with the product. The reader should consider consulting reference works or individuals who are experts in ventilation, toxicology, and/or fire prevention, as necessary to use and understand the data contained in this MSDS

To promote safe handling, customers and recipients should: 1 – notify their employees, agents, contractors, and others whom they know or suspect will use this material or the information in this MSDS and any other information regarding hazards or safety; 2 – furnish this same information to each of their customers for the product; and 3 - request their customers to notify their employees, customers and other users of the product of this information.

The information contained herein is based on the data available to Fiber Optic Center**, Inc., and is believed to be correct. However, Fiber Optic Center™, Inc. makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Fiber Optic CenterTM, Inc. assumes no responsibility for injury from the use of the product described herein.

 ${
m ilde{A}}$ ngström ${
m ilde{B}}$ ond ${
m ilde{e}}$ is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic CenterTM, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee – inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of the properties given are typical values, and are not intended for use in preparing specifications.

Rev. A

Data is subject to change without notice.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

