



Manufacturer:
ÅngströmBond®

Product Name:
ÅngströmBond® AB9715 Cyanoacrylate Adhesive Gel, Fiber Optic Ribbonization and Repitch Instant Adhesive (20g)

Manufacturer Part Number:
AB9715-20G

▶ [Click here for more details on the ÅngströmBond® AB9715 Cyanoacrylate Adhesive Gel, Fiber Optic Ribbonization and Repitch Instant Adhesive \(20g\)](#)



AB9715

ISO-9001

Product Description

Angstrombond AB9715-20G is a low blooming and low odor cyanoacrylate adhesive, and it is specially formulated for fiber optic ribbonization and repitch applications and for the assembly of a variety of plastic, metal and rubbers. Gel consistency prevents adhesive flow even on vertical surfaces. It will highly polymerize with moisture in the air for a fast cure.

Product Application

Fiber Optic Ribbonization and Repitch

Product Benefits

- Rapid set time
- Low odor
- Low bloom
- Bonds variety of plastics, metals and rubbers
- Low slumping for vertical surfaces

Typical Properties (Uncured)

Property	Value
Chemical Type	2-Methoxyethyl-2-Cyanoacrylate
Appearance	Clear gel to slightly cloudy
Viscosity @ 77°F (25°C), cP	10,000 to 30,000
Specific gravity	1.1
Flash point	See SDS

Typical Properties (Cured)

Physical Properties

Property	Value
Temperature range, °C, (°F)	-55 to 100 (-65 to 212)
Hardness, Shore D, ASTM D2240	75-85
Glass Transition Temperature (°C)	130

Typical Curing Performance

Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The table below shows the fixture time achieved on different materials at 22°C. Fixture time is defined as the time to develop a shear strength of 0.1 N/mm².

Substrate	Fixture Time (seconds)
Mild Steel	25 to 75
Aluminum	15 to 30
Acrylonitrile butadiene styrene	20 to 40
Polyvinyl chloride	20 to 40
Polycarbonate	20 to 50
Oak Wood	45 to 60
Pine Wood	45 to 65
Beech Wood	30 to 50
Nitrile-butadiene rubber	20 to 30
Paper	<5

Cure Speed vs. Bond Gap

The rate of cure will depend on the bondline gap. Thin bond lines result in high cure speeds, increasing the bond gap will decrease the rate of cure.

Typical Cured Performance

Shear Strength

Cured 24 Hours @ 22°C - tested according to ASTM D1002.

Substrate	Shear Strength, N/mm ² (psi)
Steel (grit blasted)	≥13.8 (≥2000)
Aluminum	≥6.9 (≥1000)
Acrylonitrile butadiene styrene	≥6.9 (≥1000)
Polyvinyl chloride	≥6.9 (≥1000)
Polycarbonate	≥6.9 (≥1000)
Nitrile-butadiene rubber	≥0.7 (≥100)

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice. FOC last update 6/11/2026.



Manufacturer:
ÅngströmBond®

Product Name:
ÅngströmBond® AB9715 Cyanoacrylate Adhesive Gel, Fiber Optic Ribbonization and Repitch Instant Adhesive (20g)

Manufacturer Part Number:
AB9715-20G

▶ [Click here for more details on the ÅngströmBond® AB9715 Cyanoacrylate Adhesive Gel, Fiber Optic Ribbonization and Repitch Instant Adhesive \(20g\)](#)

Technical Data Sheet AB9715

Page 2 of 2

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for Use

For best performance bond surfaces should be clean and free from grease. This product performs best in thin bond gaps (<0.05 mm).

Disassembly and Cleanup

Liquid Cyanoacrylate should not be wiped with rags or tissue. The fabric will cause polymerization and large quantities of adhesive will heat or cure causing smoke and strong irritating vapors. Always flood with excess water to clean up spill conditions.

Storage

Shelf life of the product is 12 months stored in a cool, dry location at room temperature between 59°F to 85°F (15°C to 29°C). To prevent contamination of unused adhesive, do not return product to its original container.

Extended Storage

Shelf life of the product can be extended to 18 months with refrigerated storage temperature of 40°F ± 5°F (2°C to 7°C). If stored under refrigeration, before opening, the containers must be warmed to room temperature, otherwise, water may condense into the bottle and cause hardening of the adhesive.

Manufactured by Hemon Manufacturing Inc.
Hemon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.

ÅngströmBond® is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center™, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee -- inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice. FOC last update 6/11/2026.