



Manufacturer:
ÅngströmBond

Product Name:
ÅngströmBond CrystalBond 509 - Clear

Manufacturer Part Number:
509-CLR

▶ [Click here for more details on the ÅngströmBond CrystalBond 509 - Clear](#)



ADHESIVES

The only adhesive line developed exclusively for fiber optics

CRYSTALBOND™ 509 FROM ÅNGSTRÖMBOND®
Temporary Mounting and Bonding Adhesive

Description:

509 is a temporary bonding adhesive designed for mounting objects that require dicing, polishing and other machining processes. This adhesive exhibits high bond strength to metals, glass and ceramics. When processing is complete 509 can be removed by reheating and is soluble in acetone leaving no residue

509 is an excellent choice for polishing as it minimizes clogging of diamond tools when compared to waxes. It is transparent in thin cross sections.

Typical Applications:

- Machining advanced ceramics
- Lapping and polishing optical components
- Dicing ceramic substrates and semiconductor wafers
- Dicing ferrites, glasses and piezoelectronics
- Dicing metal and optic crystals
- Mounting cross-sections for electron microscopy
- Backfilling components for mechanical support

Application Directions:

Melt material and place between substrates. Allow to cool to room temperature before beginning processing. Product can be removed by reheating above flow point or dissolving in acetone.

Typical Physical Properties:

Color	clear Amber
Description	Thermoplastic Polymer
Form :	7/8" dia x 7" stick
Softening, °C	70-75
Flow Point, °C:	135
Viscosity @ flow point, cps	6,000

CrystalBond™ is the trademark of EMS, Fort Washington PA, USA

ÅngströmBond® is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center™, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee – inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

Rev. A 9/2003

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.