

SAFETY DATA SHEET (SDS)



Manufacturer:
ÅngströmBond®

Product Name:
Covestro DeSolite® DF-0016 Optical Fiber Coating
(Splicing and Recoat Matrix Coating), UV Cure (1 oz)

Manufacturer Part Number:
COV-DF-0016-1OZ

▶ [Click here for more details on the Covestro DeSolite® DF-0016 Optical Fiber Coating \(Splicing and Recoat Matrix Coating\), UV Cure \(1 oz\)](#)

SAFETY DATA SHEET



1. Identification

Fiber Optic Center Inc. 23 Centre Street New Bedford, MA 02740 USA	TRANSPORTATION EMERGENCY	
	CALL CHEMTREC: (800) 424-9300 INTERNATIONAL: (703) 527-3887	
	NON-TRANSPORTATION	
	Emergency Phone: Call Chemtrec Information Phone: (844) 646-0545	
Product Name:	DeSolite DF-0016	
Material Number:	50024860	
Chemical Family:	UV-Curable Mixture	
Use:	Raw material for coatings, inks, adhesives, sealants, or elastomers in industrial applications	
Restrictions on use:	Do-It-Yourself Applications	

2. Hazards Identification

This product is not classified as hazardous according to OSHA HazCom 2012 (29 CFR 1910.1200).

3. Composition/Information on Ingredients

Hazardous Components

There are no hazardous components above the relevant concentration limits according to OSHA HazCom 2012.

4. First Aid Measures

Most Important Symptom(s)/Effect(s)

Acute: Not expected to cause adverse acute health effects.

Eye Contact

In case of contact, flush eyes with plenty of lukewarm water. Irrigate copiously with clean, fresh water for at least 10 minutes, holding the eyelids apart. Get medical attention if irritation develops.

Skin Contact

In case of skin contact, wash affected areas with soap and water. Wash off immediately with plenty of

Material Name: DeSolite DF-0016

Material Number: 50024860

Page: 1 of 7

Data is subject to change without notice.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

23 Centre Street • New Bedford, MA 02740 USA • focenter.com
508-992-6464 | (800) 473-4237 • sales@focenter.com



SAFETY DATA SHEET (SDS)



Manufacturer:
ÅngströmBond®

Product Name:
Covestro DeSolite® DF-0016 Optical Fiber Coating
(Splicing and Recoat Matrix Coating), UV Cure (1 oz)

Manufacturer Part Number:
COV-DF-0016-1OZ

▶ [Click here for more details on the Covestro DeSolite® DF-0016 Optical Fiber Coating \(Splicing and Recoat Matrix Coating\), UV Cure \(1 oz\)](#)

water for at least 15 minutes. Immediately remove contaminated clothing and shoes. Call a physician if irritation develops or persists. Wash clothing and shoes before reuse.

Inhalation

If inhaled, remove to fresh air. If breathing is difficult, give oxygen. If not breathing, give artificial respiration. Get medical attention.

Ingestion

If ingested, do not induce vomiting unless directed to do so by medical personnel. If a person vomits when lying on his back, place him in the recovery position. Get medical attention.

5. Firefighting Measures

Suitable Extinguishing Media: All extinguishing media are suitable.

Unsuitable Extinguishing Media No Data Available

Fire Fighting Procedure

Firefighters should be equipped with self-contained breathing apparatus to protect against potentially toxic and irritating fumes. Use cold water spray to cool fire-exposed containers to minimize the risk of rupture.

Hazardous Decomposition Products

By Fire and Thermal Decomposition: Carbon dioxide (CO₂), carbon monoxide (CO), dense black smoke, Acrylate monomers, Aldehydes, Organic acids

Unusual Fire/Explosion Hazards

Toxic and irritating gases/fumes may be given off during burning or thermal decomposition.

6. Accidental Release Measures

Spill and Leak Procedures

Cleanup personnel must use appropriate personal protective equipment. Dike or dam spilled material and control further spillage, if possible. Prevent from entering open drains and waterways. Cover spill with inert material (e. g., dry sand or earth) and collect for proper disposal.

7. Handling and Storage

Handling/Storage Precautions

Avoid breathing dust, vapor, or mist. Avoid contact with skin or clothing. Avoid contact with eyes. Use only with adequate ventilation/personal protection. Wash thoroughly after handling. Keep container closed when not in use.

Storage Temperature

Minimum: 15 °C (59 °F)

Maximum: 30 °C (86 °F)

Storage Conditions

Inhibitor only effective in the presence of oxygen. Exposure to light may cause product polymerization. Extreme heat will result in product polymerization. Protect against heat and direct sunlight.

Employee education and training in the safe use and handling of this product are required under the OSHA

Material Name: DeSolite DF-0016

Material Number: 50024860

Page: 2 of 7

Data is subject to change without notice.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

23 Centre Street • New Bedford, MA 02740 USA • focenter.com

508-992-6464 | (800) 473-4237 • sales@focenter.com



SAFETY DATA SHEET (SDS)



Manufacturer:
ÅngströmBond®

Product Name:
Covestro DeSolite® DF-0016 Optical Fiber Coating
(Splicing and Recoat Matrix Coating), UV Cure (1 oz)

Manufacturer Part Number:
COV-DF-0016-1OZ

▶ [Click here for more details on the Covestro DeSolite® DF-0016 Optical Fiber Coating \(Splicing and Recoat Matrix Coating\), UV Cure \(1 oz\)](#)

Hazard Communication Standard 29 CFR 1910.1200.

Substances to Avoid

Exothermic reaction with:, Free radical initiators, Peroxides, strong alkalis, Strong acids, Reactive metals

8. Exposure Controls/Personal Protection

The recommendations in this section should not be a substitute for a personal protective equipment (PPE) assessment performed by the employer as required by 29 CFR 1910 Subpart I.

Exposure Limits

Any component which is listed in section 3 and is not listed in this section does not have a known ACGIH TLV, OSHA PEL or supplier recommended occupational exposure limit.

Industrial Hygiene/Ventilation Measures

General dilution and local exhaust as necessary to control airborne vapors, mists, dusts and thermal decomposition products below appropriate airborne concentration standards/guidelines.

Respiratory Protection

Respiratory protection is recommended in insufficiently ventilated working areas and during heating or spraying. For components with occupational exposure limits, when workers are facing concentrations above those limits, they must use appropriate certified respirators.

Hand Protection

Ensure gloves remain in good condition during use and replace if any deterioration is observed. Permeation resistant gloves., Nitrile rubber gloves., Avoid natural rubber gloves., Do not wear PVC gloves, as PVC absorbs acrylates.

Eye Protection

Chemical safety goggles or safety glasses with side-shields.

Skin Protection

Permeation resistant clothing, Gloves, long sleeved shirts and pants.

Additional Protective Measures

Ultraviolet (UV) light source is used for curing this product. UV light can be hazardous to unprotected skin and eyes. Protective eyewear should always be worn when working in UV curing areas. Skin protection such as long sleeves, long pants, and gloves should be worn when UV lights are being used. Wear nitrile or other chemical resistant gloves to avoid skin contact when handling partially cured fabricated objects in the "green" state of cure (after initial laser cure). The fabricated objects may be handled without gloves after the object has been thoroughly washed with solvent (e.g. tripropylene glycol monomethyl ether, isopropyl alcohol) followed by exposure to UV light and/or an oven bake at temperatures above 130°C. When sanding fully cured surfaces, suitable respiratory protection for dust should be used. Good general ventilation is required when tooling or sanding to avoid inhalation of particulate matter or airborne particles. Avoid sanding or finishing parts that are not fully cured, as uncured material may cause skin sensitization or respiratory irritation. Not Noted
Employees should wash their hands and face before eating, drinking, or using tobacco products. Educate and train employees in the safe use and handling of this product. Emergency showers and eye wash stations should be available.

Material Name: DeSolite DF-0016

Material Number: 50024860

Page: 3 of 7

Data is subject to change without notice.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

23 Centre Street • New Bedford, MA 02740 USA • focenter.com

508-992-6464 | (800) 473-4237 • sales@focenter.com



SAFETY DATA SHEET (SDS)



Manufacturer:
ÅngströmBond®

Product Name:
Covestro DeSolite® DF-0016 Optical Fiber Coating
(Splicing and Recoat Matrix Coating), UV Cure (1 oz)

Manufacturer Part Number:
COV-DF-0016-1OZ

▶ [Click here for more details on the Covestro DeSolite® DF-0016 Optical Fiber Coating \(Splicing and Recoat Matrix Coating\), UV Cure \(1 oz\)](#)

9. Physical and Chemical Properties

State of Matter:	liquid
Appearance:	viscous liquid
Color:	Clear
Odor:	characteristic
Odor Threshold:	No Data Available
pH:	No Data Available
Melting Point:	
Boiling Point:	
Flash Point:	> 100 °C (> 212 °F) (closed cup)
Evaporation Rate:	No Data Available
Lower explosion limit:	No Data Available
Upper Explosion Limit:	No Data Available
Vapor Pressure:	No Data Available
Vapor Density:	No Data Available
Density:	1.54 g/cm ³ @ 20 °C (68 °F)
Relative Vapor Density:	No Data Available
Specific Gravity:	No Data Available
Solubility in Water:	No Data Available
Partition Coefficient: n-octanol/water:	No Data Available
Auto-ignition Temperature:	No Data Available
Decomposition Temperature:	Stable under recommended storage conditions. The product is chemically stable.
Unblocking Temperature:	No Data Available
Dynamic Viscosity:	> 300 mPa.s @ 20 °C (68 °F)
Kinematic Viscosity:	> 194 mm ² /s @ 20 °C (68 °F)
Bulk Density:	No Data Available
Molecular Weight:	No Data Available
Self Ignition:	not applicable

10. Stability and Reactivity

Hazardous Reactions

No hazardous reactions when stored and handled correctly.

Stability

Stable

Materials to Avoid

Exothermic reaction with: Free radical initiators, Peroxides, strong alkalis, Strong acids, Reactive metals

Conditions to Avoid

Exposure to sunlight. Product contains an inhibitor system. Must be inhibited to prevent hazardous polymerization. Inhibitor only effective in the presence of oxygen. Heat, flames and sparks.

Hazardous Decomposition Products

By Fire and Thermal Decomposition: Carbon dioxide (CO₂), carbon monoxide (CO), dense black smoke, Acrylate monomers, Aldehydes, Organic acids

11. Toxicological Information

Material Name: DeSolite DF-0016

Material Number: 50024860

Page: 4 of 7

Data is subject to change without notice.


Contact the professionals at Fiber Optic Center for a quote or to get more details.

23 Centre Street • New Bedford, MA 02740 USA • focenter.com

508-992-6464 | (800) 473-4237 • sales@focenter.com



SAFETY DATA SHEET (SDS)



Manufacturer:
ÅngströmBond®

Product Name:
Covestro DeSolite® DF-0016 Optical Fiber Coating
(Splicing and Recoat Matrix Coating), UV Cure (1 oz)

Manufacturer Part Number:
COV-DF-0016-1OZ

▶ [Click here for more details on the Covestro DeSolite® DF-0016 Optical Fiber Coating \(Splicing and Recoat Matrix Coating\), UV Cure \(1 oz\)](#)

Likely Routes of Exposure: Skin Contact
Eye Contact
Ingestion
Inhalation

Health Effects and Symptoms

Acute: Not expected to cause adverse acute health effects.

Chronic: Not expected to cause adverse chronic health effects.

Toxicity Data for: DeSolite DF-0016

Data on the product is not available.

Acute Oral Toxicity

Acute toxicity estimate: 2,490 mg/kg (Calculation method)

Acute Dermal Toxicity

Acute toxicity estimate: 2,720 mg/kg (Calculation method)

Carcinogenicity:

No carcinogenic substances as defined by IARC, NTP and/or OSHA

12. Ecological Information

Ecological Data for: DeSolite DF-0016

Data on the product is not available.

13. Disposal Considerations

Waste Disposal Method

Waste disposal should be in accordance with existing federal, state and local environmental control laws.

Empty Container Precautions

Empty containers retain product residue (dust, liquid, vapor and/or gases) and can be dangerous. Do not reuse empty container.

14. Transportation Information

Land transport (DOT)

Non-Regulated

Sea transport (IMDG)

Non-Regulated

Air transport (ICAO/IATA)

Non-Regulated

Material Name: DeSolite DF-0016

Material Number: 50024860

Page: 5 of 7

Data is subject to change without notice.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

23 Centre Street • New Bedford, MA 02740 USA • focenter.com

508-992-6464 | (800) 473-4237 • sales@focenter.com



SAFETY DATA SHEET (SDS)



Manufacturer:
ÅngströmBond®

Product Name:
Covestro DeSolite® DF-0016 Optical Fiber Coating
(Splicing and Recoat Matrix Coating), UV Cure (1 oz)

Manufacturer Part Number:
COV-DF-0016-1OZ

▶ [Click here for more details on the Covestro DeSolite® DF-0016 Optical Fiber Coating \(Splicing and Recoat Matrix Coating\), UV Cure \(1 oz\)](#)

15. Regulatory Information

United States Federal Regulations

US. Toxic Substances Control Act: This product and its components are either on the Active Portion of the TSCA Inventory or have been cleared for use under a TSCA Low Volume Exemption (LVE).

No substances are subject to TSCA 12(b) export notification requirements.

US. EPA CERCLA Hazardous Substances (40 CFR 302.4) Components:
None

SARA Section 311/312 Hazard Categories:
Refer to hazard classification information in Section 2.

US. EPA Emergency Planning and Community Right-To-Know Act (EPCRA) SARA Title III Section 302 Extremely Hazardous Substance (40 CFR 355, Appendix A) Components:
None

US. EPA Emergency Planning and Community Right-To-Know Act (EPCRA) SARA Title III Section 313 Toxic Chemicals (40 CFR 372.65) - Supplier Notification Required Components:

<u>Concentration</u>	<u>Components</u>	<u>CAS-No.</u>
<1 ppm	Hexachlorobenzene	118-74-1

US. EPA Resource Conservation and Recovery Act (RCRA) Composite List of Hazardous Wastes and Appendix VIII Hazardous Constituents (40 CFR 261):
Under RCRA, it is the responsibility of the person who generates a solid waste, as defined in 40 CFR 261.2, to determine if that waste is a hazardous waste.

State Right-To-Know Information

The following chemicals are specifically listed by individual states; other product specific health and safety data in other sections of the SDS may also be applicable for state requirements. For details on your regulatory requirements you should contact the appropriate agency in your state.

Massachusetts, New Jersey or Pennsylvania Right to Know Substance Lists:

<u>Concentration</u>	<u>Components</u>	<u>CAS-No.</u>
>=1%	Dimethacrylate	CAS# is a trade secret
>=1%	Oligomer	CAS# is a trade secret
1 - 5%	Methanone, (1-hydroxycyclohexyl)phenyl-	947-19-3
1 - 5%	2-Benzoyl-2-hydroxypropane	7473-98-5

California Proposition 65 List:

<u>Concentration</u>	<u>Components</u>	<u>CAS-No.</u>
<1 ppm	Hexachlorobenzene	118-74-1

CFATS (Chemical Facility Anti-Terrorism Standards) Chemicals

To the best of our knowledge, this product does not contain Appendix A Chemicals of Interest (COI), at or above the Screening Threshold Quantity (STQ), as defined by the Department of Homeland Security Chemical Facility Anti-terrorism Standard (CFATS, 6 CFR Part 27).

Based on information provided by our suppliers, this product is considered "DRC Conflict Free" as defined by the SEC Conflict Minerals Final Rule (Release No. 34-67716; File No. S7-40-10; Date: 2012-08-22).

Material Name: DeSolite DF-0016

Material Number: 50024860

Page: 6 of 7

Data is subject to change without notice.


Contact the professionals at Fiber Optic Center for a quote or to get more details.

23 Centre Street • New Bedford, MA 02740 USA • focenter.com

508-992-6464 | (800) 473-4237 • sales@focenter.com



SAFETY DATA SHEET (SDS)



Manufacturer:
ÅngströmBond®

Product Name:
Covestro DeSolite® DF-0016 Optical Fiber Coating
(Splicing and Recoat Matrix Coating), UV Cure (1 oz)

Manufacturer Part Number:
COV-DF-0016-1OZ

▶ [Click here for more details on the Covestro DeSolite® DF-0016 Optical Fiber Coating \(Splicing and Recoat Matrix Coating\), UV Cure \(1 oz\)](#)

16. Other Information

Version Date: 03/31/2025
SDS Version: 1.5

For more information: phone: 1-800-473-4237, fax: 1-508-991-8876. Prepared by Fiber Optic Center, Inc.

ÅngströmBond® is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center™, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee – inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes. This warranty is limited to a credit or replacement of the product only, and does not cover direct, indirect, consequential, incidental or any other type of damage resulting from the use of the product. Fiber Optic Center is not liable for any failure to observe the precautionary measures described in this SDS or for any misuse of the product.

Material Name: DeSolite DF-0016

Material Number: 50024860

Page: 7 of 7

Data is subject to change without notice.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

23 Centre Street • New Bedford, MA 02740 USA • focenter.com

508-992-6464 | (800) 473-4237 • sales@focenter.com

