



Manufacturer:

Dymax®

Product Name:

Dymax OP-24-REV-B Optical Adhesive, Optically Clear,
Hybrid UV & Heat Cure - 3ml Syringe

Manufacturer Part Number:

OP-24-REV-B-3ML



Learn More

Click here for more details on the Dymax OP-24-REV-B Optical Adhesive, Optically Clear, Hybrid UV & Heat Cure - 3ml Syringe



Multi-Cure® OP-24-REV-B Phenolic/Filled Plastics-to-Glass and Metal

APPLICATIONS	FEATURES & BENEFITS	RECOMMENDED SUBSTRATES
Bonding Glass Lenses to Metal Fixtures or Backings	- UV/Visible Light-Cure in Seconds - Impact Resistant - Excellent Adhesion to Metal and Glass	- Phenolic - ABS - Glass - Metal

Dymax OP-24-REV-B high-performance optical adhesive cures upon exposure to UV or visible light in seconds. Because of its solvent-free and rapid-cure features, it increases productivity, lowers assembly costs, and enhances worker safety. When cured with Dymax spot, beam, or flood lamps, it delivers optimum speed and performance for a variety of optical applications. This product is in full compliance with RoHS directives 2015/863/EU.

TYPICAL UNCURED PROPERTIES *			OTHER CURED PROPERTIES *		
Property	Value	Test Method	Property	Value	Test Method
Solvent Content	None - 100% Solids	N/A	Refractive Index (20°C)	1.52	ASTM D542
Appearance	Optical Clear	N/A	Boiling Water Absorption, % (2 h)	4.15	ASTM D570
Chemical Class	Acrylated Urethane	N/A	Water Absorption, % (25°C, 24 h)	1.67	ASTM D570
Soluble in	Organic Solvents	N/A	Linear Shrinkage, %	0.31	ASTM D2566
Viscosity, cP	5,000 (nominal)	ASTM D2556	Glass Transition Tg, °C	70	ASTM D5418
Shelf Life at Recommended Conditions from Date of Manufacture	18 months	N/A	CTE α_1 , $\mu\text{m}/\text{m}/^\circ\text{C}$	55	ASTM E831
CTE α_2 , $\mu\text{m}/\text{m}/^\circ\text{C}$				206	ASTM E831

CURED MECHANICAL PROPERTIES *			ADHESION	
Property	Value	Test Method	Substrate	Recommendation
Durometer Hardness	D 80	ASTM D2240	Brass	✓
Tensile at Break, MPa [psi]	23 [3,129]	ASTM D638	Copper	✓
Elongation at Break, %	23	ASTM D638	Glass	✓
Modulus of Elasticity, MPa [psi]	2463 [357,338]	ASTM D638	Poly(ethylene terephthalate)glycol	✓
			Poly(phenylene oxide)	✓
			Polyurethane	✓
			Poly(vinyl chloride) , rigid	✓
			Thermoplastic polyurethane	✓

✓ Recommended ◊ Limited Applications
⚠ Requires Surface Treatment (e.g. plasma, corona treatment, etc.)

* Not Specifications
N/A Not Applicable

© 2024 Dymax Corporation. All rights reserved.
All trademarks in this guide, except where noted, are the property of, or used under license by Dymax Corporation, U.S.A.
Technical Data Collected 09/2023 Rev01/1/2024



Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are
subject to change without notice.

**Manufacturer:**

Dymax®

Product Name:Dymax OP-24-REV-B Optical Adhesive, Optically Clear,
Hybrid UV & Heat Cure - 3ml Syringe**Manufacturer Part Number:**

OP-24-REV-B-3ML

[Learn More](#)

▶ [Click here for more details on the Dymax OP-24-REV-B Optical Adhesive, Optically Clear, Hybrid UV & Heat Cure - 3ml Syringe](#)

**OPTICAL ADHESIVES**
OP-24-REV-B Product Data Sheet**CURING GUIDELINES**

Fixture time is defined as the time to develop a shear strength of 0.1 N/mm² [10 psi] between glass slides. Actual cure time typically is 3-to-5 times fixture time.

Dymax Curing System (Intensity)	Fixture Time or Belt Speed ^A
2000-ECE (50 mW/cm ²)	1 s
5000-EC (200 mW/cm ²) ^B	1 s
BlueWave® AX-550 RediCure® 365 nm (425 mW/cm ²)	2 s
BlueWave® AX-550 PrimeCure® 385 nm (800 mW/cm ²)	1 s
BlueWave® AX-550 VisiCure® 405 nm (650 mW/cm ²)	1 s
BlueWave® 200 (10 W/cm ²)	2 s


^A Fixture times/belt speeds are typical for curing thin films through 100% UV and light-transmitting substrates. Light-obstructing substrates may require longer cure times.

^B Intensity was measured over the UVA range (320-395 nm) using a Dymax ACCU-CAL™ 50 Radiometer.

^C At 53 mm [2.1 in] focal distance. Maximum speed of conveyor is 8.2 m/min [27 ft/min]. Intensity was measured over the UVA range (320-395 nm) using the Dymax ACCU-CAL™ 160 Radiometer.

Full cure is best determined empirically by curing at different times and intensities, and measuring the corresponding change in cured properties such as tackiness, adhesion, hardness, etc. Full cure is defined as the point at which more light exposure no longer improves cured properties.

Dymax recommends that customers employ a safety factor by curing longer and/or at higher intensities than required for full cure.

LIGHT TRANSMITTANCE

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.

**Manufacturer:**

Dymax®

Product Name:Dymax OP-24-REV-B Optical Adhesive, Optically Clear,
Hybrid UV & Heat Cure - 3ml Syringe**Manufacturer Part Number:**

OP-24-REV-B-3ML

[Learn More](#)

▶ [Click here for more details on the Dymax OP-24-REV-B Optical Adhesive, Optically Clear, Hybrid UV & Heat Cure - 3ml Syringe](#)

**OPTICAL ADHESIVES
OP-24-REV-B Product Data Sheet****SECONDARY HEAT CURE**

Heat can be used as a secondary cure mechanism where the adhesive cannot be cured with light. Light curing must be done prior to heat cure. The following heat-cure schedule may be used:

Temperature	Time*
110°C [230°F]	60 minutes
120°C [250°F]	30 minutes
150°C [300°F]	15 minutes

*Note: Actual heat cure time may vary due to part configuration, volume of adhesive applied, and oven efficiency.

Dymax recommends that customers employ a safety factor by curing longer and/or at higher intensities than required for full cure.

STORAGE AND SHELF LIFE

Store the material in a cool, dark place when not in use. Do not expose to light. This product may polymerize upon prolonged exposure to ambient and artificial light. Keep covered when not in use. This material shelf life noted on page 1 of this document, when stored between 10°C (50°F) and 32°C (90°F) in the original, unopened container.

CLEAN UP

Uncured material may be removed from dispensing components and parts with organic solvents. Cured material will be impervious to many solvents and difficult to remove. Cleanup of cured material may require mechanical methods such as ultrasonic bath, water jet, vacuum tweezers, air knife, and/or warming to aid in the removal.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

*Product specifications and data are
subject to change without notice.*

**Manufacturer:**

Dymax®

Product Name:Dymax OP-24-REV-B Optical Adhesive, Optically Clear,
Hybrid UV & Heat Cure - 3ml Syringe**Manufacturer Part Number:**

OP-24-REV-B-3ML

[Learn More](#)

▶ [Click here for more details on the Dymax OP-24-REV-B Optical Adhesive, Optically Clear, Hybrid UV & Heat Cure - 3ml Syringe](#)

**OPTICAL ADHESIVES
OP-24-REV-B Product Data Sheet****GENERAL INFORMATION**

This product is intended for industrial use only. Keep out of the reach of children. Avoid breathing vapors. Avoid contact with skin, eyes, and clothing. Wear impervious gloves. Repeated or continuous skin contact with uncured material may cause irritation. Remove material from skin with soap and water. Never use organic solvents to remove material from skin and eyes. For more information on the safe handling of this material, please refer to the Safety Data Sheet before use.

The data provided in this document are based on historical testing that Dymax performed under laboratory conditions as they existed at that time and are for informational purposes only. The data are neither specifications nor guarantees of future performance in a particular application. Dymax does not guarantee that this product's properties are suitable for the user's intended purpose.

Numerous factors—including, without limitation, transport, storage, processing, the material with which the product is used, and the ultimate function or purpose for which the product was obtained—may affect the product's performance and/or may cause the product's actual behavior to deviate from its behavior in the laboratory. None of these factors are within Dymax's control. Conclusions about the behavior of the product under the user's particular conditions, and the product's suitability for a specific purpose, cannot be drawn from the information contained in this document.

It is the user's responsibility to determine (i) whether a product is suitable for the user's particular purpose or application and (ii) whether it is compatible with the user's intended manufacturing process, equipment, and methods. Under no circumstances will Dymax be liable for determining such suitability or compatibility. Before the user sells any item that incorporates Dymax's product, the user shall adequately and repetitively test the item in accordance with the user's procedures and protocols. Unless specifically agreed to in writing, Dymax will have no involvement in, and shall under no circumstances be liable for, such testing.

Dymax makes no warranties, whether express or implied, concerning the merchantability of this product or its fitness for a particular purpose. Nothing in this document should be interpreted as a warranty of any kind. Under no circumstances will Dymax be liable for any injury, loss, expense or incidental or consequential damage of any kind allegedly arising in connection with the user's handling, processing, or use of the product. It is the user's responsibility to adopt appropriate precautions and safeguards to protect persons and property from any risk arising from such handling, processing, or use.

Except as otherwise noted, all trademarks used herein are trademarks of Dymax. The "®" symbol denotes a trademark that is registered in the U.S. Patent and Trademark Office.

The contents of this document are subject to change. Unless specifically agreed to in writing, Dymax shall have no obligation to notify the user about any change to its content.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

*Product specifications and data are
subject to change without notice.*