



Manufacturer:
Epoxy Technology

Product Name:
EPO-TEK® 375 High Temperature Epoxy, Heat Cure (4g)

Manufacturer Part Number:
ET375-4G



Learn More

► Click here for more details on the EPO-TEK® 375 High Temperature Epoxy, Heat Cure (4g)



EPO-TEK® 375

Technical Data Sheet
For Reference Only
High Temperature Epoxy

Date: August 2024
Rev: X
No. of Components: Two
Mix Ratio by Weight: 10 : 1
Specific Gravity: Part A: 1.20 Part B: 1.00
Pot Life: 4 Hours
Shelf Life- Bulk: One year at room temperature
Shelf Life- Syringe: One year at -40°C

Recommended Cure: 150°C / 1 Hour

Minimum Alternative Cure(s):
May not achieve performance properties listed below
150°C / 5 Minutes
120°C / 20 Minutes
100°C / 60 Minutes
80°C / 90 Minutes

NOTES:

- Container(s) should be kept closed when not in use.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity, others) of the product may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.
- Syringe packaging will impact initial viscosity and effective pot life, potentially beyond stated parameters.
- If product crystallizes in storage, place container in warm oven until crystallization disappears.
- **TOTAL MASS SHOULD NOT EXCEED 25 GRAMS**

Product Description: EPO-TEK® 375 is a two component, high temperature epoxy designed for semiconductor, hybrid, and fiber optic applications. Also available in a single component frozen syringe.

Typical Properties: Cure condition: 150°C / 1 Hour Different batches, conditions & applications yield differing results.

Data below is not guaranteed. To be used as a guide only, not as a specification. * denotes test on lot acceptance basis

PHYSICAL PROPERTIES:			
* Color (before cure):	Part A: Clear/Colorless	Part B: Amber	
* Consistency:	Pourable liquid		
* Viscosity (23°C) @ 50 rpm:	3,000 - 5,000	cPs	
Thixotropic Index:	N/A		
* Glass Transition Temp:	≥ 100	°C (Dynamic Cure: 20-200°C/ISO 25 Min; Ramp -10-200°C @20°C/Min)	
Coefficient of Thermal Expansion (CTE):			
Below Tg:	48	x 10 ⁻⁶ in/in°C	
Above Tg:	192	x 10 ⁻⁶ in/in°C	
Shore D Hardness:	88		
Lap Shear @ 23°C:	> 2,000	psi	
Die Shear @ 23°C:	≥ 10	Kg	3,556 psi
Degradation Temp:	421	°C	
Weight Loss:			
@ 200°C:	0.06	%	
@ 250°C:	0.16	%	
@ 300°C:	0.49	%	
Suggested Operating Temperature:	< 300	°C (Intermittent)	
Storage Modulus:	339,358	psi	
Particle Size:	N/A		

ELECTRICAL AND THERMAL PROPERTIES:			
Thermal Conductivity:	N/A		
Volume Resistivity @ 23°C:	≥ 1 x 10 ¹³	Ohm-cm	
Dielectric Constant (1KHz):	3.34		
Dissipation Factor (1KHz):	0.004		

OPTICAL PROPERTIES @ 23°C:			
Spectral Transmission:	> 94% @ 600-790	nm	
	> 98% @ 800-1500	nm	
Refractive Index:	1.5692 @ 589	nm	

Epoxyes and Adhesives for Demanding Applications™

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.



Learn More



Manufacturer:
Epoxy Technology

Product Name:
EPO-TEK® 375 High Temperature Epoxy, Heat Cure (4g)

Manufacturer Part Number:
ET375-4G

▶ Click here for more details on the EPO-TEK® 375 High Temperature Epoxy, Heat Cure (4g)



EPO-TEK® 375

Technical Data Sheet
For Reference Only
High Temperature Epoxy

EPO-TEK® 375 Advantages & Suggested Application Notes:

- Reasonable pot-life that allows for low temperature curing to be realized. It has an amber color change upon cure.
- Semiconductor suggested applications: wafer-wafer bonding of CSP; fabrication of MEMs devices; flip chip underfill.
- Hybrid suggested applications: providing near hermetic seals and UHV seals in sensor devices and resisting high temperature packaging.
 - Down-hole petrochemical fiber optic sensors resisting >200°C field conditions.
- Fiber optic adhesive suggested applications:
 - Sealing fiber into ferrules, transmitting light in the optical pathway from 800- 1550 nm range.
 - Fiber component packaging, adhesive for active alignment of optics, environmental seal of opto-package, V-groove arrays.
- Electronics Assembly suggested applications:
 - Used as dielectric layer in the fabrication of capacitors; laminating PZT ferroelectrics found in ultrasound or ink-jetting devices.
 - Impregnating and insulating copper coil windings in motors and inductor coils. Bonding ferrite cores and magnets
 - Structural grade epoxy found in hard-disk drive devices; bonding of stainless steel metals, kapton, and magnets.
 - For an ISO 10993 biocompatible version, see EPO-TEK® MED-375.

Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.