



Manufacturer:
Epoxy Technology

Product Name:
EPO-TEK® HYB-353ND-TX2 High Temperature Epoxy, Hybrid Heat & UV Cure - Pre-Mixed and Frozen (3cc Syringe)

Manufacturer Part Number:
ETHYB-353ND-TX2



Learn More

Click here for more details on the EPO-TEK® HYB-353ND-TX2 High Temperature Epoxy, Hybrid Heat & UV Cure - Pre-Mixed and Frozen (3cc Syringe)



Product Information Sheet

EPO-TEK® HYB-353ND-TX2 PMF Syringe



Date: October 2022 **Rev:** VII
Material Description: A single component, high temperature hybrid epoxy for semiconductor, fiber optic and medical applications. It is designed to have similar cured performance to EPO-TEK® 353ND; modified to allow for initial UV tacking. It is a higher thixotropy version of EPO-TEK® HYB-353ND.
Number of Components: Single
Mix Ratio by Weight: N/A
Recommended Cure: Initial Tack 100mW/cm² for 10 seconds @ 240-365 nm + 150°C/30 Minutes Thermal Cure
Minimum Alternative Cure: Initial Tack 100mW/cm² for 10 seconds @ 240-365 nm + 100°C/30 Minutes Thermal Cure
Initial Tack 100mW/cm² for 10 seconds @ 240-365 nm + 80°C/1 Hour Thermal Cure
Specific Gravity: 1.14
Pot Life: < 2 Days
Shelf Life: Six months at -40°C

NOTES:

- To prevent gelation, keep containers away from light sources.
- Performance properties (rheology, conductivity, others) of the Products may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.

MATERIAL CHARACTERISTICS: Cure condition: Initial Tack 100mW/cm² for 10 seconds @ 240-365 nm + 150°C/30 Minutes
To be used as a guide only, not as a specification. Different batches, conditions and applications yield differing results.
* denotes test on lot acceptance basis Data below is not guaranteed.

PHYSICAL PROPERTIES:

* Color (before cure):

Cloudy/Light Yellow

* Consistency:

Pourable paste

* Viscosity (23°C) @ 10 rpm:

17,000-35,000 cPs

Thixotropic Index:

1.7

* Glass Transition Temp:

≥ 90 °C (Dynamic Cure:20-200°C/ISO 25 Min + Ramp -10-200°C @ 20°C/Min)

Coefficient of Thermal Expansion (CTE):

Below Tg:

63 x 10⁻⁶ in/in°C

Above Tg:

179 x 10⁻⁶ in/in°C

Shore D Hardness:

80

Die Shear @ 23°C:

≥ 15 Kg 5,334 psi

Degradation Temp:

410 °C

Weight Loss:

@ 200°C

0.05 %

@ 250°C

0.50 %

@ 300°C

1.50 %

Suggested Operating Temperature:

< 350 °C (Intermittent)

Storage Modulus:

524,311 psi

* Particle Size:

≤ 20 microns

OPTICAL PROPERTIES @ 23°C:

Spectral Transmission:

≥ 50% @ 550 nm

≥ 95% @ 1,100-1,600 nm

≥ 98% @ 800-1,000 nm

Refractive Index:

1.5457 @ 589 nm

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.