



**Manufacturer:**  
Epoxy Technology

**Product Name:**  
EPO-TEK® OG198-54 Electrically and Thermally Insulating Epoxy, UV & Heat Cure (3cc Syringe)

**Manufacturer Part Number:**  
OG198-54-3CC

▶ Click here for more details on the EPO-TEK® OG198-54 Electrically and Thermally Insulating Epoxy, UV & Heat Cure (3cc Syringe)



### EPO-TEK® OG198-54

#### Technical Data Sheet

For Reference Only

Shadow Curable UV Epoxy

**Date:** September 2023 **Rev:** XVIII  
**No. of Components:** Single  
**Specific Gravity:** 1.12  
**Pot Life:** N/A  
**Shelf Life- Bulk:** Six months refrigerated  
**Shelf Life- Syringe:** Six months refrigerated

Recommended Cure	
Iron-Doped Mercury Flood Lamp 100 mW/cm <sup>2</sup> @ 240-365 nm	> 30 sec.
Alternative Cures*	
Iron-Doped Mercury Spot Lamp	> 30 sec.
365nm LED Flood Lamp	> 30 sec.
Pulsed Mercury Lamp	> 30 sec.
<b>UV Cure is complete after 24 hours from UV Exposure</b>	
* Contact Technical Services for application-specific variations	

**NOTES:**

- Container(s) should be kept closed when not in use.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity, others) of the product may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.

**Product Description:** EPO-TEK® OG198-54 is a single component, low viscosity, electrically and thermally insulating UV cure epoxy.

**Typical Properties:** Cure condition: varies as required \*denotes test on lot acceptance basis Data below is not guaranteed. To be used as a guide only, not as a specification. Different batches, conditions & applications yield differing results.

PHYSICAL PROPERTIES:	
* Color (before cure):	Clear/Colorless
* Consistency:	Pourable liquid
* Viscosity (23°C) @ 100 rpm:	200 - 450 cPs
* Glass Transition Temp:	≥ 115 °C (Dynamic Cure:20-200°C/ISO 25 Min; Ramp -10-200°C @ 20°C/Min)
<b>Coefficient of Thermal Expansion (CTE):</b>	
Below Tg:	74 x 10 <sup>-6</sup> in/in°C
Above Tg:	145 x 10 <sup>-6</sup> in/in°C
Shore D Hardness:	86
<b>Die Shear:</b>	
UV Cure:	≥ 10 Kg 3,556 psi
UV Cure + 23°C/24 Hours:	20.8 Kg 7,396.5 psi
UV Cure + 80°C/1 Hour:	22.2 Kg 7,894.3 psi
Degradation Temp:	369 °C
<b>Weight Loss:</b>	
@ 200°C	0.24 %
@ 250°C	0.62 %
@ 300°C	1.80 %
Suggested Operating Temperature:	< 300 °C (Intermittent)
Storage Modulus:	449,431 psi
OPTICAL PROPERTIES @ 23°C:	
Spectral Transmission:	≥ 97% @ 460-1,680 nm
Refractive Index (uncured):	1.5046 @ 589 nm
Refractive Index (cured):	1.5256 @ 589 nm

**Epoxyes and Adhesives for Demanding Applications™**

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

[focenter.com](http://focenter.com) • 508-992-6464 | (800) 473-4237 • [sales@focenter.com](mailto:sales@focenter.com)

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.



**Manufacturer:**  
Epoxy Technology

**Product Name:**  
EPO-TEK® OG198-54 Electrically and Thermally Insulating Epoxy, UV & Heat Cure (3cc Syringe)

**Manufacturer Part Number:**  
OG198-54-3CC



▶ [Click here for more details on the EPO-TEK® OG198-54 Electrically and Thermally Insulating Epoxy, UV & Heat Cure \(3cc Syringe\)](#)



**EPO-TEK® OG198-54**  
Technical Data Sheet  
For Reference Only  
*Shadow Curable UV Epoxy*

**EPO-TEK® OG198-54 Advantages & Suggested Application Notes:**

- UV shadow cure allows for enhanced performance after a thermal post cure and significant cure propagation into shadow area.
- High Tg.
- Strong transmission in the Visible and IR regions.
- Suggested Applications:
  - Active alignment of optics
  - Bonding fibers to V-grooves
  - Fiber pigtailed
  - Alignment in optoelectronic hybrids
  - Semiconductor devices

**Epoxyes and Adhesives for Demanding Applications™**

**This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.**

**Contact the professionals at Fiber Optic Center for a quote or to get more details.**

[focenter.com](http://focenter.com) • 508-992-6464 | (800) 473-4237 • [sales@focenter.com](mailto:sales@focenter.com)

23 Centre Street • New Bedford, MA 02740 USA

*Product specifications and data are subject to change without notice.*