



Manufacturer:
Epoxy Technology

Product Name:
EPO-TEK® OG198-55 Electrically and Thermally Insulating Epoxy, UV & Heat Cure (3cc Syringe)

Manufacturer Part Number:
OG198-54-3CC

▶ [Click here for more details on the EPO-TEK® OG198-55 Electrically and Thermally Insulating Epoxy, UV & Heat Cure \(3cc Syringe\)](#)



EPO-TEK® OG198-55

Technical Data Sheet
For Reference Only
Shadow Curable UV Epoxy

Date: April 2022 **Rev:** X
No. of Components: Single
Specific Gravity: 1.15
Pot Life: N/A
Shelf Life- Bulk: Six months refrigerated
Shelf Life- Syringe: Six months refrigerated

NOTES:

- Container(s) should be kept closed when not in use.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity & others) may vary from those stated below when syringe packaging and/or post-processing is required.
- Thermal post-cure beneficial - contact techserv@epotek.com for recommendations.

Recommended Cure	
Iron-Doped Mercury Flood Lamp 100 mW/cm ² @ 240-365 nm	> 30 sec.
Alternative Cures*	
Iron-Doped Mercury Spot Lamp	> 30 sec.
365nm LED Flood Lamp	> 30 sec.
Pulsed Mercury Lamp	> 30 sec.
UV Cure is complete after 24 hours from UV Exposure	
* Contact Technical Services for application-specific variations	

Product Description: EPO-TEK® OG198-55 is a high viscosity, single component, electrically and thermally insulating, translucent UV cure epoxy. It is the more thixotropic version of EPO-TEK® OG198-54.

Typical Properties: Cure condition: varies as required *denotes test on lot acceptance basis Data below is not guaranteed. To be used as a guide only, not as a specification. Different batches, conditions & applications yield differing results.

PHYSICAL PROPERTIES:	
* Color (before cure):	Translucent
* Consistency:	Smooth thixotropic paste
* Viscosity (23°C): @ 100 rpm	1,200-2,000 cPs
Thixotropic Index:	6.0
* Glass Transition Temp:	≥ 120 °C (Dynamic Cure:20-200°C/ISO 25 Min; Ramp -10-200°C @ 20°C/Min)
Coefficient of Thermal Expansion (CTE):	
Below Tg:	72 x 10 ⁻⁶ in/in°C
Above Tg:	120 x 10 ⁻⁶ in/in°C
Shore D Hardness:	85
Die Shear @ 23°C:	
UV Cure:	≥ 20 Kg 7,112 psi
UV Cure + 23°C/24 Hours:	27.7 Kg 9,850.1 psi
UV Cure + 80°C/1 Hour:	27.2 Kg 9,672.3 psi
Degradation Temp:	354 °C
Weight Loss:	
@ 200°C	0.23 %
@ 250°C	0.73 %
@ 300°C	2.13 %
Suggested Operating Temperature:	< 300 °C (Intermittent)
Storage Modulus:	489,872 psi
* Particle Size:	≤ 20 microns
OPTICAL PROPERTIES @ 23°C:	
Spectral Transmission:	≥ 97% @ 560-1,680 nm
Refractive Index (uncured):	1.5023 @ 589 nm
Refractive Index (cured):	1.5196 @ 589 nm

Epoxies and Adhesives for Demanding Applications™
This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.



Manufacturer:
Epoxy Technology

Product Name:
EPO-TEK® OG198-55 Electrically and Thermally Insulating Epoxy, UV & Heat Cure (3cc Syringe)

Manufacturer Part Number:
OG198-54-3CC



▶ [Click here for more details on the EPO-TEK® OG198-55 Electrically and Thermally Insulating Epoxy, UV & Heat Cure \(3cc Syringe\)](#)



EPO-TEK® OG198-55
Technical Data Sheet
For Reference Only
Shadow Curable UV Epoxy

EPO-TEK® OG198-55 Advantages & Suggested Application Notes:

- UV shadow cure allows for enhanced performance after a thermal post cure and significant cure propagation into shadow area.
- High Tg.
- Strong transmission above 560 nm.
- Suggested Applications:
 - ◊ Active alignment of optics
 - ◊ Bonding fibers to V-grooves
 - ◊ Fiber pigtails
 - ◊ Medical devices
 - ◊ Alignment in optoelectronic hybrids
 - ◊ Semiconductor devices
 - ◊ General bonding including structural adhesive in commercial LED lighting

Epoxyes and Adhesives for Demanding Applications™

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.